

**TERPOL FR V0**

ABS

Emas Plastik San.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	12	g/10min	ISO 1133
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3250	MPa	ISO 527
Tensile Strength	30	MPa	ISO 527
Strain at break	2	%	ISO 527
Izod notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Shore D hardness	75	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	210	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Vicat softening temperature, B	100	°C	ISO 306
Burning behav. at thickness h	V-0	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	1200	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Special Characteristics**

Flame retardant