

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2250	MPa	ISO 527
Stress at break	40	MPa	ISO 527
Strain at break	9	%	ISO 527
Izod notched impact strength, +23°C	21.5	kJ/m ²	ISO 180/1A

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ISO 1183
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	200 - 230	°C	-
Mold temperature	60 - 80	°C	-
Zone 1	200 - 230	°C	-
Zone 2	200 - 230	°C	-
Zone 3	200 - 230	°C	-
Nozzle temperature	200	°C	-
Back pressure	0.1 - 0.5	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Black, Brown, Natural Color, White

Special Characteristics

Anti-static, High impact or impact modified, U.V. stabilized or stable to weather

Regional Availability

Europe, Near East/Africa