

Titan A200AS

ABS

Titan Plastics Compounds Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	45	MPa	ISO 527
Flexural modulus, 23°C	2100	MPa	ISO 178
Flexural strength	62	MPa	ISO 178
Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E9	Ohm*m	IEC 62631-3-1
Surface resistivity	1E11	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	230 - 260	°C	-
Mold temperature	60 - 80	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Anti-static, Transparent

Delivery form

Natural Color

Regional Availability

Asia Pacific