

Product Texts

This material is also produced by Toray Plastics (Malaysia).

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2500	MPa	ISO 527
Yield stress	47	MPa	ISO 527
Flexural modulus, 23°C	2280	MPa	ISO 178
Charpy notched impact strength, +23°C	25	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	81	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1040	kg/m ³	ISO 1183

Characteristics**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa