

**Product Texts**

This material is produced by Toray Plastics (Malaysia).

**Processing/Physical Characteristics**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	10	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

**Mechanical properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3100	MPa	ISO 527
Yield stress	59	MPa	ISO 527
Flexural modulus, 23°C	2830	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m <sup>2</sup>	ISO 179/1eA

**Thermal properties**

	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	98	°C	ISO 75-1/-2

**Other properties**

	Value	Unit	Test Standard
Density	1070	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Regional Availability**

North America, Europe, Asia Pacific, South and Central America