

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	49	MPa	ISO 527
Strain at break	13	%	ISO 527
Flexural modulus, 23°C	2410	MPa	ISO 178
Charpy notched impact strength, +23°C	13	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 111	-	ISO 2039-2

ASTM Data			
Tensile Strength	41	MPa	ASTM D 638
Elongation at Break	10	%	ASTM D 638
Flexural Modulus	2160	MPa	ASTM D 790
Rockwell Hardness	R 111	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	103	°C	ISO 75-1/-2
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 264 psi	107	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1070	kg/m ³	ISO 1183
Density	1070	kg/m ³	ASTM D 792

Characteristics

Additives

Lubricants

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa