

Trilliant™ HC THC-01-AS149031 Trans Blue

ABS

Avient Corporation

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	37.9	MPa	ASTM D 638
Elongation at Break	12	%	ASTM D 638
Flexural Modulus	1620	MPa	ASTM D 790
Izod Impact notched, 1/8 in	180	J/m	ASTM D 256

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Anti-static

ApplicationsIT / Business Machine, Electrical and Electronical,
Encapsulation, Medical**Regional Availability**

North America