

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>55</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>220</b>	°C	-
Molding shrinkage, parallel	<b>0.5</b>	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>2250</b>	MPa	ISO 527
Tensile Strength	<b>41</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>2450</b>	MPa	ISO 178
Flexural strength	<b>67</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>14</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	<b>R 103</b>	-	ISO 2039-2

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>79</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>90</b>	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1050</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Regional Availability**

Asia Pacific