

Witcom ABS-AS-S

ABS

Wittenburg B.V.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.7	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	36	MPa	ISO 527
Strain at break	6	%	ISO 527
Flexural modulus, 23°C	2300	MPa	ISO 178
Flexural strength	57	MPa	ISO 178
Izod impact strength, +23°C	62	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	5.5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E8	Ohm	ASTM D 257
Volume Resistivity	1E8	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Anti-static

Regional Availability

Europe