

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>7.5</b>	g/10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>7.5</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>92</b>	°C	ISO 11357-1/-3
<b>ASTM Data</b>			
Melting Temperature	<b>92</b>	°C	ASTM D 3418
Vicat Temperature	<b>54</b>	°C	ASTM D 1525
<b>Other properties</b>			
Density	<b>938</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>938</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Other Extrusion, Coating

**Delivery form**

Pellets

**Features**

Heat Sealable, Copolymer

**Certifications**

Food contact, Food approval FDA 21 CFR

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa