

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	4	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	4	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	90	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	90	°C	ASTM D 3418
Vicat Temperature	68	°C	ASTM D 1525
Other properties			
Density	980	kg/m ³	ISO 1183
Density	980	kg/m ³	ASTM D 792

Characteristics

Processing

Blown Film Extrusion, Other Extrusion

Delivery form

Pellets

Features

Heat Sealable, Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa