

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7.3	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	7.3	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	92	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	92	°C	ASTM D 3418
Vicat Temperature	54	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1000	kg/m ³	ISO 1183
Density	1000	kg/m ³	ASTM D 792

Characteristics

Processing
Blown Film Extrusion, Other Extrusion, Coating

Delivery form
Pellets

Features
Heat Sealable, Copolymer

Certifications
Food contact, Food approval FDA 21 CFR

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa