

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>3.6</b>	g/10min	ISO 1133
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>3.6</b>	g/10min	ASTM D 1238
Temperature	<b>190</b>	°C	-
Load	<b>2.16</b>	kg	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>94</b>	°C	ISO 11357-1/-3
<b>ASTM Data</b>			
Melting Temperature	<b>94</b>	°C	ASTM D 3418
Vicat Temperature	<b>68</b>	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	<b>941</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>941</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Blown Film Extrusion, Film Extrusion

**Delivery form**

Pellets

**Features**

Good Adhesion, Heat Sealable, Copolymer

**Certifications**

Food contact, Food approval FDA 21 CFR

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa