

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	8.9	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	8.9	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	75	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	75	°C	ASTM D 3418
Vicat Temperature	49	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	960	kg/m ³	ISO 1183
Density	960	kg/m ³	ASTM D 792

Characteristics

Processing

Film Extrusion

Delivery form

Pellets

Features

Heat Sealable, Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa