

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	5.5	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	5.5	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	94	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	94	°C	ASTM D 3418
Other properties			
Density	940	kg/m ³	ISO 1183
Density	940	kg/m ³	ASTM D 792

Characteristics

Processing

Blown Film Extrusion, Coating

Delivery form

Pellets

Special Characteristics

Transparent

Features

Good Adhesion, Heat Sealable, Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Packaging

Regional Availability

Asia Pacific