

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	32	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
<b>ASTM Data</b>			
Melt Flow Index, MFI	32	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	81	°C	ISO 11357-1/-3
<b>ASTM Data</b>			
Melting Temperature	81	°C	ASTM D 3418
Vicat Temperature	49	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	970	kg/m <sup>3</sup>	ISO 1183
Density	970	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**  
Coating

**Delivery form**  
Pellets

**Special Characteristics**  
Transparent

**Features**  
Good Adhesion, Heat Sealable, Copolymer

**Certifications**  
Food contact, Food approval FDA 21 CFR

**Applications**  
Packaging

**Regional Availability**  
Asia Pacific