

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	96	°C	ISO 11357-1/-3
ASTM Data			
Melting Temperature	96	°C	ASTM D 3418
Vicat Temperature	58	°C	ASTM D 1525
Other properties			
Density	920	kg/m ³	ISO 1183
Density	920	kg/m ³	ASTM D 792

Characteristics

Processing

Coating

Delivery form

Pellets

Special Characteristics

Transparent

Features

Good Adhesion, Heat Sealable, Copolymer

Applications

Packaging

Regional Availability

Asia Pacific