

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|-------------------------------------|-------|---------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 2 | g/10min | ASTM D 1238 |
| Temperature | 190 | °C | - |
| Load | 2.16 | kg | - |

| Thermal properties | Value | Unit | Test Standard |
|---------------------|-------|------|---------------|
| ASTM Data | | | |
| Melting Temperature | 104 | °C | ASTM D 3418 |

| Other properties | Value | Unit | Test Standard |
|------------------|-------|-------------------|---------------|
| Density | 928 | kg/m ³ | ASTM D 792 |

| Film Properties | Value | Unit | Test Standard |
|-------------------------------|-------|------|---------------|
| ASTM Data | | | |
| Tensile Strength at Break, MD | 28 | MPa | ASTM D 882 |
| Tensile Strength at Break, TD | 22 | MPa | ASTM D 882 |
| Elongation at Break, MD | 310 | % | ASTM D 882 |
| Elongation at Break, TD | 520 | % | ASTM D 882 |

Characteristics

Processing

Film Extrusion

Special Characteristics

Transparent

Features

Foamable, Copolymer

Applications

Packaging

Regional Availability

Europe, Asia Pacific, Near East/Africa