

**SIVERAS® LX70T45**

LCP-(GF+MD)45

Toray Industries, Inc.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>130</b>	MPa	ASTM D 638
Elongation at Break	<b>3</b>	%	ASTM D 638
Flexural Modulus	<b>14500</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>60</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>0.38</b>	mm	-
Coefficient of Thermal Expansion, MD	<b>15</b>	E-6/K	ASTM D 696
DTUL @ 264 psi	<b>250</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1750</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Special Characteristics**

High impact or impact modified

**Features**

Low Warpage

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa