

LAPEROS™ GA481

LCP-(MD+GF)45

Polyplastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	12000	MPa	ISO 178
Flexural strength	145	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Strength	100	MPa	ASTM D 638
Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	265	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Yellow Card available	yes	-	-
Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.8	-	IEC 62631-2-1
Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1
Electric strength	45	kV/mm	IEC 60243-1
Comparative tracking index	175	-	IEC 60112
ASTM Data			
Arc Resistance	182	s	ASTM D 495
Other properties	Value	Unit	Test Standard
Density	1770	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Flame retardant

Regional Availability

Asia Pacific

Features

Low Warpage