

VECTRA® V400P

LCP

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	14400	MPa	ISO 527
^[C] Stress at break	151	MPa	ISO 527
^[C] Strain at break	1.62	%	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	111	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Humidity absorption	0.04	%	Sim. to ISO 62
^[C] Density	1400	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Regional Availability**

North America, Europe, Asia Pacific