

Product Texts

Exceptional strength and stiffness. Suitable for metal replacement applications. Electrically conductive. 30% carbon fiber reinforced. Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant UL-Listing V-0 at 0.46mm thickness per UL 94 flame testing. Relative-Temperature-Index (RTI) according to UL 746B: electrical 130°C, mechanical 130°C. UL = Underwriters Laboratories (USA)

Flammability at thickness h V-0 -

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|------------|------|-----------------|
| ISO Data | | | |
| ^[C] Molding shrinkage, normal | 0.1 | % | ISO 294-4, 2577 |

[C]: CAMPUS

| Mechanical properties | Value | Unit | Test Standard |
|--|--------------|-------------------|---------------|
| ISO Data | | | |
| ^[C] Tensile Modulus | 31800 | MPa | ISO 527 |
| ^[C] Stress at break | 200 | MPa | ISO 527 |
| ^[C] Strain at break | 0.7 | % | ISO 527 |
| ^[C] Charpy impact strength, +23°C | 15 | kJ/m ² | ISO 179/1eU |
| ^[C] Charpy notched impact strength, +23°C | 6 | kJ/m ² | ISO 179/1eA |

[C]: CAMPUS

| Thermal properties | Value | Unit | Test Standard |
|--|------------|-------|-----------------|
| ISO Data | | | |
| ^[C] Melting temperature, 10°C/min | 280 | °C | ISO 11357-1/-3 |
| ^[C] Temp. of deflection under load, 1.80 MPa | 235 | °C | ISO 75-1/-2 |
| ^[C] Temp. of deflection under load, 0.45 MPa | 250 | °C | ISO 75-1/-2 |
| ^[C] Vicat softening temperature, B | 167 | °C | ISO 306 |
| ^[C] Coeff. of linear therm. expansion, parallel | 1 | E-6/K | ISO 11359-1/-2 |
| ^[C] Coeff. of linear therm. expansion, normal | 9 | E-6/K | ISO 11359-1/-2 |
| ^[C] Burning Behav. at thickness h | V-0 | class | IEC 60695-11-10 |

[C]: CAMPUS

| Electrical properties | Value | Unit | Test Standard |
|--|-------------|-------|---------------|
| ISO Data | | | |
| ^[C] Relative permittivity, 1MHz | 32 | - | IEC 62631-2-1 |
| ^[C] Volume resistivity | 1000 | Ohm*m | IEC 62631-3-1 |
| ^[C] Surface resistivity | 100 | Ohm | IEC 62631-3-2 |

[C]: CAMPUS

| Other properties | Value | Unit | Test Standard |
|------------------------|-------------|-------------------|---------------|
| ^[C] Density | 1500 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Increased electrical conductivity, Anti-static, Flame retardant, Light stabilized or stable to light

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

Vectra resins are well known for their excellent thermal and hydrolytic stability. In order to ensure these properties are optimum, the resin should be dried correctly prior to processing. Vectra B-grades should be dried at 150 C for a minimum of 6 hours in a desiccant dryer.

A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller machines: 1/2 feed, 1/4 compression, 1/4 metering.

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the molder can increase the injection velocity to improve melt flow.