

Product Texts

Vectra® MT1345 VF3001 (natural) is a 30% mineral filled, easy flow LCP grade for injection molding.

Vectra® MT1345 VF3001 (natural) is a special grade developed for medical industry applications and complies with:

- Food Contact Substance Notification (FCN) No. 742 of the Food and Drug Administration (FDA) and is listed in the Drug Master File (DMF 8464) and the Device Master File (MAF 315)
- the corresponding EU and national registry regulatory requirements
- biocompatibility in tests corresponding to USP 23 Class VI/ISO 10993
- low residual monomers
- no animal products

Best overall surface appearance with properties similar to MT1310. Less abrasive than glass fiber reinforced grades. Improved toughness over MT1310. Outstanding hydrolytic stability. Recommended where aesthetics are key.

Chemical abbreviation according to ISO 1043-1 : LCP

Inherently flame retardant.

Flammability at thickness h V-0 -

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11000	MPa	ISO 527
^[C] Stress at break	180	MPa	ISO 527
^[C] Strain at break	2.5	%	ISO 527
^[C] Charpy notched impact strength, +23°C	45	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	280	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	190	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	203	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	151	°C	ISO 306
^[C] Coeff. of linear therm. expansion, parallel	13	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	77	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 100Hz	3.8	-	IEC 62631-2-1
^[C] Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
^[C] Dissipation factor, 100Hz	100	E-4	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	160	E-4	IEC 62631-2-1
^[C] Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	44	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1650	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Special Characteristics

Flame retardant, Light stabilized or stable to light

Chemical Resistance

Hydrolytically Stable

Certifications

Food contact notification (FCN), Medical Grade, US Pharmacopeia Class VI Approved, Drug Master File, Device Master File

Applications

Medical

Regional Availability

North America, Europe

Other text information

Injection molding

Vectra resins are well known for their excellent thermal and hydrolytic stability. In order to ensure these properties are optimum, the resin should be dried correctly prior to processing. The Vectra MT-grades MT1300, MT1305, MT1310, MT1335, MT1340 and MT1345 should be dried at 150°C for a minimum of 4 hours in a desiccant dryer.

A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller machines: 1/2 feed, 1/4 compression, 1/4 metering.

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the molder can increase the injection velocity to improve melt flow.