

VECTRA® S540

LCP-GB40

Celanese

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9000	MPa	ISO 527
^[C] Stress at break	100	MPa	ISO 527
^[C] Strain at break	3	%	ISO 527
^[C] Charpy impact strength, +23°C	13	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	350	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	275	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Humidity absorption	0.003	%	Sim. to ISO 62
^[C] Density	1740	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Regional Availability**

North America, Europe, Asia Pacific