

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.001	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	12410	MPa	ASTM D 638
Tensile Strength	103	MPa	ASTM D 638
Flexural Modulus	12410	MPa	ASTM D 790
Flexural Strength	148	MPa	ASTM D 790
Izod Impact notched, 1/8 in	107	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	274	°C	ASTM D 648
DTUL @ 264 psi	232	°C	ASTM D 648
Other properties			
Density	1740	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	8	h	-
Melt temperature	332 - 366	°C	-
Mold temperature	65.6 - 121	°C	-
Injection pressure	82.7 - 124	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Platable