

SUMIKASUPER® SZ6712L

LCP-MX60

Sumitomo Chemical Co., Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0032	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0075	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	85	MPa	ASTM D 638
Flexural Modulus	10400	MPa	ASTM D 790
Flexural Strength	110	MPa	ASTM D 790
Izod Impact unnotched, 1/8 in	140	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	240	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	2210	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	130	°C	-
Pre-drying - Time	4 - 24	h	-
Melt temperature	330	°C	-
Mold temperature	40 - 160	°C	-
Zone 1	280 - 320	°C	-
Zone 2	300 - 340	°C	-
Zone 3	320 - 360	°C	-
Nozzle temperature	320 - 360	°C	-
Screw speed	50 - 100	rpm	-
Injection pressure	80 - 160	MPa	-
Back pressure	1 - 5	MPa	-
Holding pressure	20 - 60	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Delivery form

White