

Product Texts

Easy flow high impact MABS grade

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	24	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1700	MPa	ISO 527
^[C] Yield stress	41	MPa	ISO 527
^[C] Yield strain	3.5	%	ISO 527
^[C] Charpy impact strength, +23°C	88	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	13	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	73	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	93	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1090	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	70	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	200 - 240	°C	-
Mold temperature	40 - 80	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Granules

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

PREPROCESSING; Pretreatment

Predrying: 2-4h / 70°C

PROCESSING ;Processing:

Melttemperature	200 - 240	°C
Mouldtemperature	40 - 80	°C