

STAREX SF-0950

MABS

Lotte Chemical Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	13	g/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
ASTM Data			
Melt Flow Index, MFI	13	g/10min	ASTM D 1238
Temperature	220	°C	-
Load	10	kg	-
Mold Shrinkage, MD	0.0045	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.0045	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Tensile Modulus	2600	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Stress at break	40	MPa	ISO 527
Flexural modulus, 23°C	2700	MPa	ISO 178
Flexural strength	85	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	9	kJ/m ²	ISO 180/1A
Rockwell hardness	R 116	-	ISO 2039-2
ASTM Data			
Tensile Modulus	2500	MPa	ASTM D 638
Tensile Strength at Yield	51	MPa	ASTM D 638
Tensile Strength at Break	34	MPa	ASTM D 638
Flexural Modulus	2600	MPa	ASTM D 790
Flexural Strength	74	MPa	ASTM D 790
Rockwell Hardness	R 116	-	ASTM D 785
Izod Impact notched, 1/8 in	110	J/m	ASTM D 256
Izod Impact notched, 1/4 in	98	J/m	ASTM D 256
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	78	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	91	°C	ISO 75-1/-2
Vicat softening temperature, B	100	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 66 psi	98	°C	ASTM D 648
DTUL @ 264 psi	92	°C	ASTM D 648
Other properties			
Density	1100	kg/m ³	ISO 1183
Density	1100	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	85	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	240	°C	-

STAREX SF-0950

MABS

Lotte Chemical Corporation

Mold temperature	60	°C	-
Zone 1	200 - 210	°C	-
Zone 2	210 - 220	°C	-
Zone 3	230	°C	-
Nozzle temperature	240	°C	-
Screw speed	30 - 70	rpm	-
Back pressure	0.5 - 2	MPa	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific