

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.1 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.1 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2250 / -	MPa	ISO 527
^[C] Stress at break	53 / -	MPa	ISO 527
^[C] Strain at break	>50 / -	%	ISO 527
Flexural modulus, 23°C	2150 / -	MPa	ISO 178
^[C] Charpy notched impact strength, +23°C	63 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	225 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	70 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	105 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1080 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Natural Color

Applications

Sports Equipment