

Product Texts

Product-nomenclature ISO 16396-PA12,GF30,M1H,C18-040

Product Attributes

Improved friction & wear properties, Improved heat resistance

Markets

Automotive

Automotive electr. and electronics, lighting

Electricals & Electronics

Electrical appliances, Electrical equipment

Industry & Consumer goods

Mechanical Engineering, Tools & Accessories

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.7 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	4000 / 3000	MPa	ISO 527
^[C] Stress at break	60 / 50	MPa	ISO 527
^[C] Strain at break	8 / 10	%	ISO 527
^[C] Charpy impact strength, +23°C	60 / 70	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	60 / 60	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	6 / 6	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	6 / 6	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	178 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	105 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 8.00 MPa	50 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	40 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	90 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E9 / 1E9	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
^[C] Electric strength	39 / 43	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 600	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	1 / *	%	Sim. to ISO 62
^[C] Humidity absorption	0.5 / *	%	Sim. to ISO 62
^[C] Density	1240 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Granules, Black

Special Characteristics

Heat stabilized or stable to heat

Features

Tribologic Grade

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa