

PlusTek PD4301G6GR

PA12-GF30

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.8	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	130	MPa	ISO 527
Strain at break	4.4	%	ISO 527
Izod notched impact strength, +23°C	15	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Water absorption	1.5	%	Sim. to ISO 62
Humidity absorption	0.7	%	Sim. to ISO 62
Density	1270	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Mold temperature	60 - 80	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	220 - 230	°C	-
Zone 2	220 - 230	°C	-
Zone 3	230 - 250	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Features

High Coefficient of Friction

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa