

**Product Texts**

long fiber reinforced

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>11720</b>	MPa	ASTM D 638
Tensile Strength	<b>162</b>	MPa	ASTM D 638
Elongation at Yield	<b>2</b>	%	ASTM D 638
Flexural Modulus	<b>8274</b>	MPa	ASTM D 790
Flexural Strength	<b>255</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>427</b>	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	<b>1490</b>	J/m	ASTM D 256

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1460</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Features**

Long fiber reinforced

**Regional Availability**

North America, Europe, Asia Pacific