

**Product Texts**

Product-nomenclature: ISO 16396-PA12/MACMI PA12,,GHLT,C14-020

Co Polyamide

Transparent Polyamide

**Product Attributes**

Improved alcohol resistance, Improved impact resistance, Highly transparent

**Markets**

**Automotive**

Automotive electr. and electronics, lighting, Cooling and climate control, Fuel systems, Powertrain and Chassis, Interior

**Electricals & Electronics**

Electrical appliances, Electrical equipment, Cables & Tubes, Energy distribution, Mobile phones and other portable devices, Lighting

**Industry & Consumer goods**

Housewares, Hydraulics & Pneumatics, Mechanical Engineering, Medical devices, Power transmission,

Sanitary, water and gas supply, Sports & Leisure, Tools & Accessories

**Optics**

Optical components, Sunglasses, Spectacle frames

**Approvals**

**Burning Behaviour**

UL V2

**Medical**

ISO 10993

**Potable Water Contact**

NSF 61

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.5 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	980	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.2	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	2200	J/(kg K)	-
<sup>[C]</sup> Eff. thermal diffusivity	9.28E-8	m <sup>2</sup> /s	-
<sup>[C]</sup> Ejection temperature	115	°C	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2000 / 1900	MPa	ISO 527
<sup>[C]</sup> Yield stress	75 / 70	MPa	ISO 527
<sup>[C]</sup> Yield strain	7 / 6	%	ISO 527
<sup>[C]</sup> Nominal strain at break	>50 / >50	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	9 / 9	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	8 / 8	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Shore D hardness	83 / *	-	ISO 7619-1

[C]: CAMPUS

**Grilamid TR 55 LX natural**

PA12/MACMI

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Glass transition temperature, 10°C/min	<b>110 / *</b>	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>80 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>90 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>90 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	<b>90 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	<b>1E11 / 1E11</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>* / 1E12</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>32 / 32</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>- / 600</b>	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>2.5 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>1 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1040 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Injection Molding, melt temperature	<b>265</b>	°C	ISO 294
Injection Molding, mold temperature	<b>30</b>	°C	ISO 294
Injection Molding, injection velocity	<b>250</b>	mm/s	ISO 294
Injection Molding, pressure at hold	<b>75</b>	MPa	ISO 294

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Delivery form**

Granules, Natural Color

**Special Characteristics**

High impact or impact modified, Transparent

**Features**

Copolymer

**Certifications**

Drinking water contact, Drinking water contact NSF 61, Biocompatibility ISO 10993

**Applications**

Automotive, Electrical and Electronical, Medical, Sports Equipment

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information****Other extrusion**

-- PIPE EXTRUSION --

-- SHEATING --

PROCESSING

Melt temperature : 250-270 °C

Feeding bush : 60-90

Barrel temp. profile : 240-250 °C

Head temp. : 250-240 °C

Please consider the information about the application of the materials.