

Product Texts

Radiopaque compound.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	9700	MPa	ISO 527
Stress at break	35	MPa	ISO 527
Strain at break	0.8	%	ISO 527
Charpy impact strength, +23°C	15	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA

Thermal properties

	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	110	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	170	°C	ISO 75-1/-2
Vicat softening temperature, B	165	°C	ISO 306

Electrical properties

	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	100	Ohm	ASTM D 257
Volume Resistivity	1000	Ohm*cm	ASTM D 257

Other properties

	Value	Unit	Test Standard
Density	4260	kg/m ³	ISO 1183

Processing Recommendation Injection Molding

	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	250 - 270	°C	-
Mold temperature	70 - 90	°C	-

Characteristics**Processing**

Injection Molding