

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8900 / 4900	MPa	ISO 527
^[C] Stress at break	168 / 100	MPa	ISO 527
^[C] Strain at break	3.3 / 4.7	%	ISO 527
^[C] Charpy impact strength, +23°C	70 / 90	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	10 / 16	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	229 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1360 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding