

| Mechanical properties                                | dry / cond         | Unit              | Test Standard |
|--|--------------------|-------------------|---------------|
| <b>ISO Data</b>                                      |                    |                   |               |
| <sup>[C]</sup> Tensile Modulus                       | <b>5800 / 4400</b> | MPa               | ISO 527       |
| <sup>[C]</sup> Stress at break                       | <b>80 / 57</b>     | MPa               | ISO 527       |
| <sup>[C]</sup> Strain at break                       | <b>2.3 / 6.1</b>   | %                 | ISO 527       |
| <sup>[C]</sup> Charpy impact strength, +23°C         | <b>17 / 20</b>     | kJ/m <sup>2</sup> | ISO 179/1eU   |
| <sup>[C]</sup> Charpy notched impact strength, +23°C | <b>2 / 2</b>       | kJ/m <sup>2</sup> | ISO 179/1eA   |

[C]: CAMPUS

| Thermal properties                                      | dry / cond    | Unit | Test Standard |
|---|---------------|------|---------------|
| <b>ISO Data</b>   |               |      |               |
| <sup>[C]</sup> Temp. of deflection under load, 1.80 MPa | <b>91 / *</b> | °C   | ISO 75-1/-2   |

[C]: CAMPUS

| Other properties       | dry / cond      | Unit              | Test Standard |
|------------------------|-----------------|-------------------|---------------|
| <sup>[C]</sup> Density | <b>1550 / -</b> | kg/m <sup>3</sup> | ISO 1183      |

[C]: CAMPUS

## Characteristics

### Processing

Injection Molding

### Regional Availability

North America, Europe, Asia Pacific, Near East/Africa