

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	17000 / 13700	MPa	ISO 527
^[C] Stress at break	245 / 185	MPa	ISO 527
^[C] Strain at break	2.5 / 3.3	%	ISO 527
^[C] Charpy impact strength, +23°C	95 / 93	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	15 / 17	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	245 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1600 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa