

**AKROMID® B3 GF 15 1 L black (4670)**

(PA6+PP)-GF15

Akro-Plastic GmbH

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	15 / *	cm <sup>3</sup> /10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	5200 / 3700	MPa	ISO 527
Stress at break	105 / 65	MPa	ISO 527
Strain at break	3.3 / 5.3	%	ISO 527
Charpy impact strength, +23°C	60 / 55	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	60 / 60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	10 / 12	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	6 / 6	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	192 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	27 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	142 / *	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Glow Wire Flammability Index (GWFI)	700	°C	IEC 60695-2-12
GWFI - thickness tested (1)	0.8	mm	-
Glow Wire Ignition Temperature (GWIT)	725	°C	IEC 60695-2-13
GWIT - thickness tested (1)	0.8	mm	-

Other properties	dry / cond	Unit	Test Standard
Density	1140 / -	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	270	°C	-
Mold temperature	80	°C	-
Injection pressure	75	MPa	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Black

**Special Characteristics**

Heat stabilized or stable to heat

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

Europe, Asia Pacific