

**Product Texts**

Base Polymer	Polyamide 6
Filler	20% carbon fiber
Colour	natural (carbon optic)
Special Features	medium viscosity
Market Segment	Automotive, Sport

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	50 / *	cm <sup>3</sup> /10min	ISO 1133
Temperature	300 / *	°C	-
Load	1.2 / *	kg	-
Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5 / *	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	15500 / 8200	MPa	ISO 527
Tensile Strength	190 / 106	MPa	ISO 527
Strain at break	1.9 / 4.8	%	ISO 527
Flexural modulus, 23°C	13100 / -	MPa	ISO 178
Flexural strength	280 / -	MPa	ISO 178
Charpy impact strength, +23°C	58 / 70	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	7 / 12	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	207 / *	°C	ISO 75-1/-2

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	1 / -	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 100	Ohm	IEC 62631-3-2

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1230 / -	kg/m <sup>3</sup>	ISO 1183
Global warming potential	5.72	kg CO <sub>2</sub> eq./kg	ISO 14040, 14044

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 8	h	-
Processing humidity	≤0.12	%	-
Melt temperature	250 - 270	°C	-
Mold temperature	60 - 100	°C	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Natural Color

**Applications**

Automotive, Sports Equipment

**Regional Availability**

Europe