

PlusTek PB341S50NT

PA6-GB50

Polyram

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	4600	MPa	ISO 527
Tensile Strength	60	MPa	ISO 527
Strain at break	7	%	ISO 527
Flexural modulus, 23°C	4500	MPa	ISO 178
Flexural strength	95	MPa	ISO 178
Charpy notched impact strength, -30°C	4	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Water absorption	5	%	Sim. to ISO 62
Humidity absorption	1.5	%	Sim. to ISO 62
Density	1530	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.15	%	-
Mold temperature	90 - 95	°C	-
Feed temperature	60 - 70	°C	-
Zone 1	290 - 300	°C	-
Zone 2	290 - 300	°C	-
Zone 3	290 - 300	°C	-

Characteristics**Processing**

Injection Molding

Certifications

RoHS compliant

Delivery form

Natural Color

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Special Characteristics

Heat stabilized or stable to heat