

Product Texts

LNP LUBRICOMP PFL26 compound is based on Nylon 6 resin containing 30% glass fiber, 10% PTFE. Added features of this grade include: Wear Resistant

UL Yellow Card Link [E45329-103600532](https://www.ulprospector.com/usa/Products/Plastics/PA6+PTFE-GF30)

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	10200	MPa	ISO 527
Stress at break	250	MPa	ISO 527
Strain at break	4.2	%	ISO 527
Flexural modulus	8600	MPa	ISO 178
Izod impact strength, +23°C, 4mm	98	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	14	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	206	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	219	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	24	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	75	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

Other properties	Value	Unit	Test Standard
Density	1440	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific