

**POLIMID LUB B 3015 GFTF**

(PA6+PTFE)-GF30

Poliblend S.p.a.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	8000	MPa	ISO 527
Stress at break	145	MPa	ISO 527
Strain at break	2	%	ISO 527
Izod notched impact strength, +23°C	7.5	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	222	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	208	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	218	°C	ISO 75-1/-2
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
<b>Other properties</b>			
Density	1490	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Additives**

Lubricants

**Regional Availability**

Europe