

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6500	MPa	ISO 527
^[C] Stress at break	130	MPa	ISO 527
^[C] Strain at break	2.5	%	ISO 527
^[C] Charpy impact strength, +23°C	37	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	4.6	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	199	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1240	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form

Black