

RTP 207 A TFE 15 HB

(PA6+PTFE)-GF40

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.00125	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	12760	MPa	ASTM D 638
Tensile Strength	148	MPa	ASTM D 638
Flexural Modulus	12070	MPa	ASTM D 790
Flexural Strength	248	MPa	ASTM D 790
Izod Impact notched, 1/8 in	123	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.559	mm	-
DTUL @ 264 psi	204	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1610	kg/m ³	ASTM D 792
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	82.2	°C	-
Pre-drying - Time	2	h	-
Melt temperature	243 - 279	°C	-
Mold temperature	54.4 - 93.3	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Additives

Lubricants

Regional Availability

North America, Europe, Asia Pacific