

DOMAMID 6G16I2UV1 505

PA6-GF15

DOMO Engineering Plastics

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	5100	MPa	ISO 527
Stress at break	100	MPa	ISO 527
Strain at break	4	%	ISO 527
Flexural modulus, 23°C	4300	MPa	ISO 178
Charpy impact strength, +23°C	70	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	70	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	16	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	9	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	221	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	185	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	205	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Electrical properties			
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	500	-	IEC 60112
Other properties			
Density	1200	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	240 - 260	°C	-
Mold temperature	80 - 90	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather