

**RTP 200 C TFE 10**

(PA11+PTFE)

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.02	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	1379	MPa	ASTM D 638
Tensile Strength	34.5	MPa	ASTM D 638
Flexural Modulus	1379	MPa	ASTM D 790
Flexural Strength	51.7	MPa	ASTM D 790
Izod Impact notched, 1/8 in	69.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	54.4	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Biobased content	89	%	-
Density	1090	kg/m <sup>3</sup>	ASTM D 792
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	79.4	°C	-
Pre-drying - Time	4	h	-
Melt temperature	224 - 288	°C	-
Mold temperature	37.8 - 65.6	°C	-
Injection pressure	68.9 - 103	MPa	-

**Characteristics****Processing**

Injection Molding

**Certifications**

Contains renewable resources

**Additives**

Lubricants

**Regional Availability**

North America, Europe, Asia Pacific