

RTP 284 C TFE 15
(PA11+PTFE)-CF25

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.002	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	14130	MPa	ASTM D 638
Tensile Strength	145	MPa	ASTM D 638
Flexural Modulus	11380	MPa	ASTM D 790
Flexural Strength	214	MPa	ASTM D 790
Izod Impact notched, 1/8 in	203	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	204	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Volume Resistivity	1	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Biobased content	58	%	-
Density	1260	kg/m ³	ASTM D 792
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	79.4	°C	-
Pre-drying - Time	4	h	-
Melt temperature	224 - 288	°C	-
Mold temperature	37.8 - 65.6	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics

Processing

Injection Molding

Additives

Lubricants

Certifications

Contains renewable resources

Regional Availability

North America, Europe, Asia Pacific