

Product Texts

PA6 15% glass fibre reinforced injection moulding grade. Heat stabilized. Improved UV resistance. Black colour.

Suitable for parts requiring improved stiffness, good heat ageing resistance and which must also resist to outdoor exposure.

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6300 / -	MPa	ISO 527
^[C] Stress at break	120 / -	MPa	ISO 527
^[C] Strain at break	2.5 / -	%	ISO 527
^[C] Charpy impact strength, +23°C	35 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	5.5 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / 1E11	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1240 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Granules, Black

Additives

Release agent

Special Characteristics

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature	Mold Temperature	Injection Speed
240 - 280°C	80 - 90°C	medium-high