

Wellamid® GFT1525-BK

PA6-GF15

Wellman Advanced Materials

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	100	MPa	ISO 527
Flexural modulus, 23°C	4300	MPa	ISO 178
Flexural strength	145	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	195	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Regional Availability

North America

Special Characteristics

High impact or impact modified