

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	6000 / 3300	MPa	ISO 527
^[C] Stress at break	120 / 70	MPa	ISO 527
^[C] Strain at break	3.5 / 8.7	%	ISO 527
Flexural modulus, 23°C	5500 / 3000	MPa	ISO 178
^[C] Charpy impact strength, +23°C	75 / 80	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	80 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	13 / 20	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	7.5 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	192 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	100 / -	Ohm*m	IEC 62631-3-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1230 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing
Injection Molding

Delivery form
Natural Color

Special Characteristics
High impact or impact modified

Applications
Sports Equipment